



CORROSION BLOCK®

High Performance
GREASE
 Multi Purpose
 Won't Soften, Breakdown or Wash Out

APPLICATIONS

CORROSION BLOCK GREASE PERFORMANCE DATA

MARINE:

Winches, Pulleys, Battery terminals, Trailer hitch, bearings, rollers & casters, Trim tabs, Inboard/ Outboard drives, Turnbuckles, Sea cocks, Y valves, Windlasses, Canvas snaps & zippers, Auto pilot mechanisms, Locks, Davits, Prop shafts, Fishing reels & guides, Hinges, Light sockets, Steering mechanisms, Electric motors & connectors, Throttle linkages & shift controls, Roller furling gear, Sail track, Gear box's, Blocks & cam cleats.

AUTOMOTIVE:

All purpose chassis lube, Disk brake & caliper assembly grease, Parts lubricant, Bearing grease, Battery terminals, Gear regulators and tracks, Linkages, Hinges and locks, Hubs, Axles, Springs, Wiring harnesses, CV joints, Antilock braking systems, Fifth wheel hitch.

RECREATIONAL:

Bicycles, Trailers, Hitches, Running Lights, Fitness equipment, Mopeds, Running machines, In-line skate bearings, skateboards, Ski bindings, ATV's, Jet ski, Motorcycles, Snow Mobile (Chassis points), Hunting gear & guns, Fishing equipment.

INDUSTRIAL:

Plain and anti-friction bearings, Deep drawing application, Ball and roller bearings, Electronic equipment, Fans, Wheel bearings, Farm equipment, Food processing equipment, Ovens, Chassis points, Cables, Gaming machines, Mining equipment, Electric motor bearings, Satellite antenna motor drive & assembly, Switch assemblies, Freezers, Conveyer assemblies, Valves, Blowers, Cams, Slides, Chains, Water pumps & valves, Paving Equipment, Snow removal equipment, Open gears, Vending machines & Parking meters.

Properties	Test Method	Found
4-Ball Wear Test - Scar Diameter	ASTM D-2266	0.40mm
4-Ball EP - Load Wear Index	ASTM D-2596	100
4- Ball EP - Weld Point	ASTM D-2596	500kg
Rust Protection	ASTM D-1743	PASS
Wheel Bearing Life	ASTM D-3527	276hrs
Water Washout @ 175°F	ASTM D-1264	2.0wt%
Mobility @ 0°F	USS	12g/min.
Low Temperature Torque @ -40 °C	ASTM D-4693	6.7 Nm
Color and Appearance	Visual	Smooth, Aqua
N.L.G.I. Grade	ASTM D-217	2
Dropping Point	ASTM D-2265	520°F/271°C
Base Oil Viscosity, @104°F / 40°C	ASTM D-445	126 cSt
Base Oil Viscosity, @ 212°F / 100°C	ASTM D-445	11.7 cSt
Penetration @25°C - Unworked	ASTM D-217	278
Penetration @25°C - 60 Strokes	ASTM D-217	280
Penetration @25°C - 100,000 Strokes	ASTM D-217	293
Timken OK Load	ASTM D-2509	60 lbs

All technical information, recommendations and statements contained here in are based on tests Lear Chemical believes to be reliable. It is offered in good faith but with no guarantee. Lear Chemical makes no warranty expressed or implied as to the suitability of our product for any particular use in operations not under our direct control. Liability is limited to the net purchase price of the product.
 Lear Chemical Research Corp.©



LEAR CHEMICAL RESEARCH CORPORATION

P.O. Box 1040 Station B, Mississauga, ON L4Y 3W3
 1-800-BLOCK-IT (256-2548) / Inter.(905)564-0018
 FAX: (905) 564-7077

Internet: <http://www.learchem.com> Email: sales@learchem.com

